

EPOXY FLOW 100 SLOW SET



Epoxy Flow 100 Slow is our 100 percent solids clear epoxy with a great floor life...meaning you can work with it on the floor for a long time...up to 45 minutes! Our customers are loving this for large projects, metallic floors, and for those who just want more time. This product can be tinted with pigment for solid color floors, mixed with metallic pigments, used as a broadcast coat.




PRODUCT HIGHLIGHTS

- 45+ Minute pot life for more comfortable application.
- Excellent clarity, leveling and reflective properties.
- Can be tinted for solid color applications

Typical Properties & Technical Information

PROPERTY	VALUE
Solids/Active Content, Percentage by weight	100%
Dry Time - Tack Free	11 - 13 Hours
Dry Time - Foot Traffic	20 - 24 Hours
Dry Time - Heavy Traffic	2 - 7 Days
Re-Coat Time Window	12 - 24 Hours
Application Temperature	50°F - 80°F
VOC (Volatile Organic Compound) Content	Less than 50 grams/Liter
Appearance - Wet	Clear (May show slight haze)
Appearance - Dry	Clear and High Gloss

Information above is based on lab temperatures of 70° - 72°F at 50% RH. Using this product outside these conditions may affect the accuracy of the information above. Always test prior to use!



APPROXIMATE COVERAGE RATES

First Coat: 100-150 ft² per gallon
 Second Coat - Over existing coating: 75 - 125 ft² per gallon
 Metallic Coat - Over existing coating: 40 - 100 ft² per gallon

*Coverage rates may vary depending upon surface porosity, texture, application method and prior sealer application. Excessive build up should be avoided.

EPOXY FLOW 100 SLOW SET



Shelf Life

Epoxy Flow 100 Slow Set has shelf life of up to one year from manufacture date in its original, unopened container stored at room temperature.

Packaging

Epoxy Flow 100 Slow Set is packaged available in 1.5 & 3 gallon kits.

Instructions For Use

MOISTURE TESTING: Concrete floors, especially those not poured over a proper vapor barrier (plastic), are subject to possible moisture vapor transmission which may result in bubbling and/or failure of high performance coatings. Basic moisture testing can be performed by placing a 4' x 4' sheet of plastic on the concrete surface and securely taping it down on all edges. If after 24 hours the concrete is still dry below the plastic, the surface should be ready to coat. If moisture is present, the coating applicator should perform calcium chloride and relative humidity probe testing to determine if excessive levels of vapor emissions are present before applying any coatings.

SURFACE PREPARATION: The concrete surface must be deemed mechanically and structurally sound, thoroughly clean of debris and completely dry. Concrete must be fully cured a minimum of 28 days. It is recommended to prepare the concrete surface by mechanical means such as shot blasting or diamond grinding with 30 grit or coarser diamonds to achieve a CSP-2 to CSP-3 profile. Vacuum concrete surface several times until dust thoroughly removed. If applying over an existing, fully bonded coating that is outside its recommended recoat window, the surface should be sanded thoroughly with a 60-120 grit sanding screen until the surface is completely dulled with scratches. Vacuum dust thoroughly, rinse with clean water and remove excess water with a wet/dry vacuum or floor scrubber. Allow surface to dry completely prior to application of coating. Where applicable and with adequate ventilation, wipe the surface with acetone and a microfiber dust mop. **CAUTION:** Acetone is extremely flammable! If using acetone follow all safety precautions, make sure no pilot lights, open flames, sources of static electricity, sparks or extreme heat sources are present. Use recommended personal protection for acetone.

Substrate, air and material temperatures must be no less than 50°F and not exceed 80°F. If applied outside these limits the coating may not achieve adequate film formation and may have excessive air entrapment, bubbles, blushing or hazing. Please note that higher substrate, air and material temperatures as well as excessive humidity may speed the cure rate of this product. Cooler temperatures and lower humidity may slow the cure rate of this product.

FOR PERSONAL PROTECTION USE GLOVES, GOGGLES, RESPIRATOR AND OTHER NECESSARY PPE. REFER TO SDS PRIOR TO USE!

TINTING: Tint with epoxy pigment. One pint container per 3 gallon kit is suggested for a solid, opaque finish. For metallic epoxy applications, one quart container of metallic pigment per 3 gallon kit is suggested. Always add color to Part A and drill mix for 2-3 minutes prior to blending A and B. Color may settle during long term storage and be difficult to redistribute. Always test for color acceptance prior to full application. Multiple coats may be necessary for total opacity. Refer to physical color chart for color selection.

MIXING: If mixing less than a full kit, mix Part A and Part B separately with a stir stick, low speed mixer or vigorously shake containers prior to measuring out the smaller kit to ensure uniform distribution of all ingredients. In a clean mixing container, blend 2 Parts A and 1 Part B using a drill mixer for 2-3 minutes. If mixing a full kit (except a 15 gallon kit), the Part A container can be used as the mixing container. Avoid creating a vortex in the material which could introduce air and/or moisture content to the mixture. Do not mix more than can be applied within the usable pot life time frame. **DO NOT THIN!**

APPLICATION: It is suggested to apply the mixed material by pouring it out onto the surface and spread with a flat flexible squeegee or a notched squeegee. Don't let mixed material sit in the bucket. Use a 1/8" (8 - 12 mil) notched squeegee when applying direct to concrete. A 3/16" (15 - 20 mil) to 1/4" (25 - 30 mil) notched squeegee may be used on additional coats over a completely sealed off surface. Back roll clear and solid color epoxy using 3/8" nap shedless roller or 3/8" foam roller. 18" rollers are recommended for any surface to speed up application time and reduce roller marks. For metallic applications, refer to metallic pigment data sheet for more information. Use a brush or small roller for corners and areas hard to maneuver longer squeegees/rollers. While applying keep a wet edge to prevent roller marks. It is recommended to work in sections usually using control joints as dividers to ensure proper application results. It is always suggested to minimize the amount of time mixed material is held in a larger volume, especially in higher temperatures. If the material becomes thick while applying and sticking to the application tools, stop applying and discard the mixed material. At this point it has reached the end of the usable pot life. While applying keep a wet edge to prevent streaking. Do not allow to puddle! Use a brush to remove excess coating in joints.

RECOATING: If possible, recoat within the suggested recoat window located on page 1. Apply additional coats in the same manner as the first coat. Note that higher substrate, air and material temperatures as well as excessive humidity may greatly reduce the acceptable recoat window of this product. When working in higher temperatures, always recoat as early in the recoat window as possible to avoid failure between coats. If recoating outside the suggested recoat window (see page 1) or beyond 24 hours, sand using a 60-120 grit sanding screen to ensure adequate adhesion between coats. Vacuum dust thoroughly, rinse with clean water and remove excess water with a wet/dry vacuum or floor scrubber. Allow surface to dry completely prior to application of coating. Where applicable and with adequate ventilation, wipe the surface with acetone and a microfiber dust mop. **CAUTION:** Acetone is extremely flammable! If using acetone follow all safety precautions, make sure no pilot lights, open flames, sources of static electricity, sparks or extreme heat sources are present. Use recommended personal protection for acetone.

PLEASE NOTE: Applying material outside the suggested parameters may result in product failure. It is always recommended to test the product in a small, inconspicuous area (on the same concrete substrate) for desired results prior to application. Coverage rates may vary for all coatings and substrates depending on porosity, density, texture etc. When applying, adhere to suggested coverage rates. Applying too thin of a coating may cause inadequate film formation, limited performance expectations and/or undesirable finish. Applying too thick may result to bubbling, hazing, etc. **DO NOT USE ON BRICK.**

COF WARNING: OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slip-resistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. Concrete Floor Supply recommends the use of slip-resistant aggregate in all coatings or flooring systems that may be exposed to wet, oily or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. Concrete Floor Supply, nor its sales agents will be responsible for injury incurred in a slip and fall accident.

Clean Up

Use MEK. Dispose of containers in accordance with local, state and federal regulations.

Product Removal

Dried, cured sealer may be removed with a commercial epoxy stripper or by using a diamond grinding method, sandblasting method or similar mechanical action.

Precautions and Limitations

- This product will freeze during storage. Store at temperatures above 40°F.
- All HVAC ventilation ducts should be somehow blocked prior to application so solvent fumes are not distributed.
- Use proper ventilation while applying and for hours after application to ensure fumes are removed.
- This product, specifically Part B is corrosive. Wear proper safety equipment while handling material.
- It is not recommended to apply product over carpet, tile, or other types of floor adhesives.
- Please be aware that this product when cured may be slippery when wet. An anti-slip additive can be added to reduce slip hazards.
- All new concrete must be cured for at least 28 days prior to application.
- It is not recommended to thin product. Improper thinning may cause sealer to delaminate in a short time frame.
- This product may darken the surface of many new and existing concrete slabs. Test prior to use.
- Physical properties listed on this technical data sheet are typical values not specifications.
- This product is not UV stable and should not be used outdoors or in areas exposed to excessive sunlight.

Special Notes

Please consult Safety Data Sheets (SDS) and read warranty information prior to use. This information can be requested by contacting customer service at 844-599-2319.

Warranty

Super Z LLC dba Concrete Floor Supply warrants that our products and the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products and uses is not a representation or a warranty. It is supplied on the condition that you will make your own tests to determine the suitability of the product for your own particular purpose.

Any use or application is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications.

Concrete Floor Supply MAKES NO WARRANTY OR GUARANTEE, EXPRESSED OR IMPLIED, RELATING TO THE PRODUCTS AND THEIR APPLICATION. THIS INCLUDES WARRANTIES OF FITNESS, DESIGN COMPATIBILITY OR MERCHANTABILITY FOR ANY PARTICULAR USE AND SHALL HAVE NO RESPONSIBILITY OR LIABILITY, INCLUDING DIRECT, INDIRECT OR CONSEQUENTIAL DAMAGES, DUE TO INJURY, DELAY OR THIRD PARTY CLAIMS FOR INSTALLATION OR REPAIR.

Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. Upon receipt of merchandise, purchaser has 30 days to notify Concrete Floor Supply in writing that the materials are defective. Defective product means that it is not merchantable and has not been used. Claims after 30 days of purchase are void. Should any of Concrete Floor Supply products prove to be defective within the 30 days from the purchase date, Concrete Floor Supply, at its sole discretion will either replace the material, issue a credit, or provide a refund for the initial paid purchase price of the material.

Certain Products may contain chemicals which may cause serious physical injury. Before using, read the Materials Safety Data Sheet and follow all precautions to prevent harm.